



SKF LGMT 3/180

General purpose industrial and automotive bearing grease

A mineral oil based, lithium soap thickened grease. This premium quality, general purpose grease is suitable for a wide range of industrial and automotive applications requiring stiff grease.

Technical specifications

Dimensions	
Corrosion protection, Emcor, ISO 11007, Distilled water	0-0

Performance	
Suitable for High load applications	● ● ● ● ●
Suitable for Vertical shaft applications	● ● ● ● ●
Suitable for applications with Oscilating movements	● ● ● ● ●
Suitable for applications with Severe vibrations	● ● ● ● ●
Suitable for applications that require Rust protection	● ● ● ● ●
Suitable for applications that require Water resistance	● ● ● ● ●
Suitable for applications that require Frequent start-up	● ● ● ● ●
Operating temperature range	Array °C
Load Range	Low - Medium C/P > 8
Speed Range	Medium
Dropping point (min) ISO 2176	180 °C
Penetration DIN ISO 2137, Worked, 60 strokes (10 ⁻¹ mm)	220 - 250
Penetration DIN ISO 2137, Prolonged (max.), 100 000 strokes, 10 ⁻¹ mm	280
Mechanical stability - Roll stability, ASTM D1831 (max.) 50 hrs at 80°C, 10 ⁻¹ mm	295
Mechanical stability, V2F test, 144 hrs	M
Corrosion protection, Emcor, ISO 11007 modified, Water washout	0-0
Corrosion protection, Emcor, ISO 11007 modified, 0.5% NaCl	-
Water resistance (max.) DIN 51807/1, 3 hrs at 90 °C	1
Oil separation DIN 51817, 40°C, %	1-3
Lubrication ability, R2F test B at 120°C	Pass
Copper corrosion (max.) DIN 51811 /ASTM D4048, 24 hrs at 100°C	2 max.at 130°C
Rolling bearing grease life (max.) ROF test, L50 life, 10000 r/min, hrs at °C	1000 at 130°C

Properties	
Category	Bearing grease
Lubricant	LGMT 3
NLGI consistency class	3
Base oil viscosity DIN 51562 at 40 °C	125 mm²/s
Base oil viscosity DIN 51562 at 100 °C	12 mm²/s
Biodegradable	No
DIN 51825 code	K3K-30
Thickener	Lithium
Colour	Amber
Base oil type	Mineral
Shelf life	5 year
Packsize	180 kg drum
Available for single point lubrication	yes

Logistics	
Product net weight	180 kg
eClass code	23-06-01-01

