



SKF LGWA 2/50

Wide temperature range, extreme pressure, high load bearing grease

A premium quality mineral oil based, lithium complex grease with extreme pressure (EP) performance. LGWA 2 is recommended for industrial and automotive applications when loads or temperatures exceed the range of general purpose greases.

Technical specifications

Dimensions	
Corrosion protection, Emcor, ISO 11007, Distilled water	0-0

Performance	
Suitable for High load applications	● ● ● ● ●
Suitable for Vertical shaft applications	● ● ● ● ●
Suitable for applications with Oscilating movements	● ● ● ● ●
Suitable for applications with Severe vibrations	● ● ● ● ●
Suitable for applications that require Rust protection	● ● ● ● ●
Suitable for applications that require Water resistance	● ● ● ● ●
Suitable for applications that require Frequent start-up	● ● ● ● ●
Operating temperature range	Array °C
Load Range	Low - High C/P > 4
Speed Range	Low - Medium
Dropping point (min) ISO 2176	250 °C
Penetration DIN ISO 2137, Worked, 60 strokes (10 ⁻¹ mm)	265 - 295
Penetration DIN ISO 2137, Prolonged (max.), 100 000 strokes, 10 ⁻¹ mm	+50
Mechanical stability - Roll stability, ASTM D1831 (max.) 50 hrs at 80°C, 10 ⁻¹ mm	+50
Mechanical stability, V2F test, 144 hrs	M
Corrosion protection, Emcor, ISO 11007 modified, Water washout	0-0
Corrosion protection, Emcor, ISO 11007 modified, 0.5% NaCl	-
Water resistance (max.) DIN 51807/1, 3 hrs at 90 °C	1
Oil separation DIN 51817, 40°C, %	1-5
Lubrication ability, R2F test B at 120°C	Pass at 100°C
Copper corrosion (max.) DIN 51811 /ASTM D4048, 24 hrs at 100°C	2 max.
Rolling bearing grease life (max.) ROF test, L50 life, 10000 r/min, hrs at °C	min. 1000 at 130°C
EP performance - 4 ball - Wear scar (max.) DIN 51350/5, 1400N	1.8 mm
EP performance - 4 ball - Weld load (min.) DIN 51350/4	2600 N

Properties	
Recommended applications	Fans and electric motors;Conveyor head and tail pulley bearings
Category	Bearing grease
Lubricant	LGWA 2
NLGI consistency class	2
Base oil viscosity DIN 51562 at 40 °C	250 mm²/s
Base oil viscosity DIN 51562 at 100 °C	17 mm²/s
Biodegradable	No
DIN 51825 code	KP2N-30
Thickener	Lithium complex
Colour	Amber
Base oil type	Mineral
Shelf life	5 year
Available for single point lubrication	yes

Logistics	
Product net weight	50 kg
eClass code	23-06-01-01
UNSPSC code	15121902